



LWP5BB-157

Poly-crystalline Silicon Solar Cell





Product Features >

 Dimension:
 156.75mmx156.75mm±0.25mm, Φ220.0mm±0.25mm

 Thickness:
 200μm±20μm

 Front side:
 0.7mm wide bus bars,Silicon nitride anti-reflection coating

 Back side:
 1.7mm wide bus bars,Silicon nitride coating

Product Characteristics

- > High conversion efficiency with high reliability
- No light-induced degradation
- Uniform cell performance with stable process control
- Low breakage rate by using high qualified and stable wafers
- > Low mismatch of cell performance during encapsulation
- Excellent power generation performance under low irradiation

Quality Control

- > Proper inspection through incoming production, outgoing and packaging
- ➤ Efficiency tested within ± 0.1% accuracy
- > 100% checked for reverse current and visual appearance
- > Reference cell calibrated from Fraunhofer
- > ISO 9001,ISO 14001 and CE,CQC etc certificated





Electric Performance >

Eff(%)	Pmpp(W)	Umpp(V)	Impp(A)	Uoc(V)	Isc(A)
19.20%	4.72	0.548	8.616	0.643	9.091
19.10%	4.69	0.546	8.590	0.642	9.061
19.00%	4.67	0.545	8.560	0.641	9.027
18.90%	4.64	0.544	8.537	0.640	9.005
18.80%	4.62	0.542	8.516	0.638	8.985
18.70%	4.59	0.541	8.494	0.637	8.964
18.60%	4.57	0.539	8.473	0.635	8.945
18.50%	4.55	0.538	8.447	0.634	8.921
18.40%	4.52	0.537	8.421	0.632	8.897
18.30%	4.50	0.535	8.380	0.631	8.866
18.20%	4.47	0.533	8.355	0.630	8.829


- •Under standard test condition: 1000W/ m², AM 1.5G, 25°C
- •Average accuracy of all tests is +/-1.5% rel

Temperature Coefficients >

Current Temperature Coefficient	Tkcurrent: +0.04%/K
Voltage Temperature Coefficient	Tk _{Voltage} : -0.31 %/K
Voltage Temperature Coefficient	Tk _{Power} : -0.39%/K

IV Curve >

Spectral Response (SR) >



LIGHTWAY ENERGY TECHNOLOGY LIMITED

 $\textbf{FAB 1:} \quad \text{Huacheng/Huifu Rd,Jintan District,Changzhou,Jiangsu,P.R.China}$

FAB 2: Medicine Industrial Park, Yuangzhou District, Yichun, Jiangxi, P.R. China

FAB 3: Xicheng Industrial Park, Baotian Rd, Xixiang Town, Shenzhen, P.R. China

Version 2017.03 @2017 Lightway Energy Technology Limited All rights reserved.