


LWM5BB-BiFi-SE-210

PERC-Mono-crystalline Silicon Bifacial Solar Cell



Product Features >


Dimension:	156.75mmx156.75mm±0.25mm, Φ210.0mm±0.25mm
Thickness:	190μm±20μm
Front side:	0.7mm wide bus bars,Silicon nitride anti-reflection coating
Back side:	1.75mm wide bus bars,Silicon nitride coating

Product Characteristics

- High conversion efficiency with high reliability
- No light-induced degradation
- Both sides can generate electricity
- Low breakage rate by using high qualified and stable wafers
- Low mismatch of cell performance during encapsulation
- Excellent power generation performance under low irradiation
- Low hot spot effect

Quality Control

- Proper inspection through incoming production, outgoing and packaging
- Efficiency tested within ± 0.1% accuracy
- 100% checked for reverse current and visual appearance
- Reference cell calibrated from Fraunhofer
- ISO 9001,ISO 14001 and CE,CQC etc certificated



Electric Performance >

Eff(%)	Pmpp(W)	Ump(V)	I _{mp} (A)	U _{oc} (V)	I _{sc} (A)
21.90%	5.35	0.578	9.258	0.673	9.742
21.80%	5.33	0.577	9.232	0.672	9.715
21.70%	5.30	0.576	9.201	0.671	9.675
21.60%	5.28	0.575	9.186	0.670	9.661
21.50%	5.25	0.572	9.181	0.667	9.657
21.40%	5.23	0.571	9.157	0.666	9.633
21.30%	5.20	0.569	9.149	0.665	9.611
21.20%	5.18	0.568	9.121	0.665	9.601
21.10%	5.16	0.567	9.096	0.664	9.589
21.00%	5.13	0.565	9.077	0.663	9.557
20.90%	5.11	0.564	9.060	0.662	9.531

●Under standard test condition: 1000W/ m², AM 1.5G, 25°C

●Average accuracy of all tests is +/-1.5% rel

Temperature Coefficients >

Current Temperature Coefficient

Tk_{Current}: +0.04%/K


Voltage Temperature Coefficient

Tk_{Voltage}: -0.32 %/K


Voltage Temperature Coefficient

Tk_{Power}: -0.42%/K

IV Curve >



Spectral Response (SR) >



LIGHTWAY ENERGY TECHNOLOGY LIMITED

FAB 1: Huacheng/Huifu Rd, Jintan District, Changzhou, Jiangsu, P.R.China

FAB 2: Medicine Industrial Park, Yuangzhou District, Yichun, Jiangxi, P.R.China

FAB 3: Xicheng Industrial Park, Baotian Rd, Xixiang Town, Shenzhen, P.R.China



Version 2017.10 @2017 Lightway Energy Technology Limited All rights reserved.